# **EUCON HC R4**



# WATER REDUCING/SET RETARDING ADMIXTURE

#### **DESCRIPTION**

Eucon HC R4 is a water reducing and retarding admixture for concrete. This versatile admixture consists of a modified carboxylate polymer which produces high quality concrete economically. Eucon HC R4 shows improved finishing characteristics and provides homogeneous concrete.

### **PRIMARY APPLICATIONS**

- Used for all cement types.
- Concrete made with SCM
- Architectural concrete

- General purpose ready mix concrete.
- Hot weather concreting
- Mass concrete / Flowable concrete

#### **FEATURES/BENEFITS**

#### **Plastic Concrete**

- Improves finishability
- Improves workability
- · Reduces water requirement

#### **Hardened Concrete**

- Increases compressive strength
- Reduces permeability
- Improves finished appearance
- Reduces shrinkage
- Increases durability

#### **TECHNICAL INFORMATION**

TEST TYPE	METHOD
Physical state	Straw yellow to brown liquid
Base material	Modified polycarboxylate
Specific Gravity	$1.08 \pm 0.02$ at $25^{\circ}$ C
Air entrainment	1.5% over control mix
рН	Minimum 6
Chloride Content	< 0.2%

Compatible with all cement types like OPC, OPC +fly ash, OPC + Slag, PPC etc.,

#### **PACKAGING**

EUCON HC R4 is packaged in bulk 220 kg and 20 kg drums.

#### **SHELF LIFE**

1 year in original, unopened package.

#### **SPECIFICATIONS/COMPLIANCES**

EUCON HC R4 meets or exceeds the requirements of:

- · IS 9103/2007
- ASTM C 494, Type G
- AASHTO M 194

## **DIRECTIONS FOR USE**

Normal dosage range is 200ml – 700ml / 50 kg of cement. However the optimum dosage is determined by site trials. EUCON HC R4 should be added to the initial batch water of the concrete mixture. Do not dispense onto dry cement. Overdosing leads to retardation of setting times of concrete, mix may segregate and bleeding of concrete.

#### **PRECAUTIONS/LIMITATIONS**

- Care should be taken to maintain EUCON HC R4 above freezing; however, freezing and subsequent thawing
  will not harm the material if thoroughly agitated. Never agitate with air or an air lance.
- Add to mix independent of other admixtures.
- In all the cases, refer Safety Data sheet before use.

WARRANTY: Flowcrete India Private Limited solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Flowcrete India Private Limited no other representations or statements made by Flowcrete India or its representatives, in writing or orally, shall alter this warranty. Flowcrete India MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Flowcrete India product fails to conform with this warranty, Flowcrete India will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any installation of Flowcrete India products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Flowcrete India's products for the Buyer's intended purposes.