# EUCON HC WATER REDUCING/SET RETARDING ADMIXTURE



# **DESCRIPTION**

Eucon HC is a water reducing and retarding admixture for concrete. This versatile admixture consists of a modified carboxylate polymer which produces high quality concrete economically. Eucon HC shows improved finishing characteristics and provides homogeneous concrete.

# **PRIMARY APPLICATIONS**

- Used for all cement types.
- Concrete made with SCM
- Architectural concrete

- · General purpose ready mix concrete.
- Hot weather concreting
- Mass concrete / Flowable concrete

# **FEATURES/BENEFITS**

#### **Plastic Concrete**

- Improves finishability
- Improves workability
- Reduces water requirement

# **Hardened Concrete**

- Increases compressive strength
- Reduces permeability
- Improves finished appearance
- Reduces shrinkage
- · Increases durability

# **TECHNICAL INFORMATION**

	METHOD
Physical state	Straw yellow to brown liquid
Base material	Modified polycarboxylate
Specific Gravity	$1.06 \pm 0.02$ at $25^{\circ}$ C
Air entrainment	1.5% over control mix
рН	Minimum 6
Chloride Content	< 0.2%

Compatible with all cement types like OPC, OPC +fly ash, PPC etc.,

#### **PACKAGING**

EUCON HC is packaged in bulk 220 kg and 20 kg drums.

# SHELF LIFE

1 year in original, unopened package.

# **SPECIFICATIONS/COMPLIANCES**

- EUCON HC meets or exceeds the requirements of:
- IS 9103/2007
- ASTM C 494, Type G
- AASHTO M 194

#### Flowcrete India Pvt Ltd

# **DIRECTIONS FOR USE**

Normal dosage range is 200ml - 700ml / 50 kg of cement. However the optimum dosage is determined by site trials. EUCON HC should be added to the initial batch water of the concrete mixture. Do not dispense onto dry cement. Overdosing leads to retardation of setting times of concrete, mix may segregate and bleeding of concrete.

# **PRECAUTIONS/LIMITATIONS**

- Care should be taken to maintain EUCON HC above freezing; however, freezing and subsequent thawing will not harm the material if thoroughly agitated. Never agitate with air or an air lance.
- · Add to mix independent of other admixtures.
- In all the cases, refer Safety Data sheet before use.